

RAKU-TOOL[®] EP-2300 / EH-2930

Modeling Paste

Multipurpose Paste

PC - Rev.-Status: 01- 2009/06/26

Page 1 of 2

Key Properties

- Easily shaped with wood working tools
- Good adhesion to most supporting structures

Applications

- Styling and Design models
- Master models
- Patterns

Processing Properties

			EP-2300	EH-2930
Color	visual		Brown	Brown
Mix ratio		parts by weight	100	100
		parts by volume	100	100
Density	ISO 1183	g/cm ³	0.63	0.64

			EP-2300 / EH-2930
Pot life at 25 °C	1000 ml	min	60
Layer thickness		mm	40
Workable after (at 25°C)		h	16

Cured / Mechanical Properties

Cure: 7 days at RT or 14h at 40°C			EP-2300 / EH-2930
Appearance	visual		Brown
Density	ISO 1183	g/cm ³	0.65
Shore hardness D	ISO 868		55-60
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	55-60
Deflection temperature, HDT	ISO 75	°C	45-50
Glass Transition temperature, Tg	DSC	°C	55-60
Compressive strength	ISO 604	MPa	23-28
Compressive modulus	ISO 604	MPa	1000-1500
Flexural strength	ISO 178	MPa	23-28
Flexural modulus	ISO 178	MPa	800-900

RAKU-TOOL® EP-2300 / EH-2930

Modelling Paste

Multipurpose Paste

PC - Rev.-Status: 01- 2009/06/26

Page 2 of 2

Processing

The processing and material temperature should be between 20-25 °C, never below 18 °C.

Mix the two components thoroughly in the ratio indicated.

Avoid applying over 40 mm at once, for thicker layers it is recommended to apply the 2nd layer after the first one has gelled.

Small quantities can be mixed by hand (with a strong wooden spatula). For larger quantities the use of a mixing machine is recommended.

Packaging

RAKU-TOOL® EP-2300	15 kg
RAKU-TOOL® EH-2930	15 kg

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
